



Figure 3. EDAX analysis results for ZnO, Mg(OH)₂, CaCO₃ and SiO₂

CONCLUSION

Wear is the loss of material from the rubbing surfaces and its calculate quantity, by weight or volume or size reduction. Wear is the loss of material from the rubbing surfaces and it can be calculated quantity, weight and volume or size reduction. In this study; high density polyethylene incorporated nano powders were found to improve wear rate. Contribution rates have increased abrasion values. All material contribution rate, the highest values were observed in the highest wear. ZnO - HDPE composite materials for wear values increased about 20%. This increase was determined at Mg (OH)₂ at 27%, 109% in the addition of SiO₂, 126% of CaCO₃ filler respectively. Finally, it seen that wear rate of SiO₂ did not change at %20. It is understood that the SiO₂ nano-fill is not effective after this at 15%. After this work, researcher can work on filled new rate and their statistical analyses.

REFERENCE

Ray SS, Okamoto M. (2003). Polymer/layered silicate nanocomposites: a review from preparation to processing, *Prog Polym Sci*, (pp. 1539-1641)
 Wang, Y., Shi, J., Han L., Xiang F. (2009). Crystallization and mechanical properties of T-ZnOw/HDPE composites, *Mater Sci Eng A*, (pp. 220-228).
 Rotheron, R. N. (1995). Particulate-Filled Polymer Composites; *Longman Scientific and Technical*: Harlow.
 Rotheron, R. N. (1999). Mineral fillers in thermoplastics: filler manufacture and characterization, *Adv Polym Sci*, (pp. 67-107).

- Ersoy S., Taşdemir, M. (2012). Properties of polymer composites filled with SiO₂, ZnO and Mg(OH)₂ nano powder, *15th International Conference on Experimental Mechanics*, Rio de Janeiro, Brezil
- Ersoy, S. (2015). Friction And Wear Performance Of High Density Polyethylene / Styrene - Butadiene Rubber Polymer Blends, *Revista Romana de Materiale* (pp. 267-271).
- Shailesh K. Dhoke, S.K.; Bhandari, R.; Khanna, A.S. (2009). Effect of Nano – ZnO Addition on The Silicone-Modified Alkyd-Based Waterborne Coatings on Its Mechanical and Heat-Resistance Properties. *Progress in Organic Coatings* (pp. 39-46).
- Saçakli, Y., Taşdemir, M. (2012) The Properties of Polymer Composites filled with Mg(OH)₂ Powder. *Journal of Polymer Materials*, (pp. 9-20).
- Elansezhian, R.; Saravanan, L. (2011). Effect of Nano Silica Fillers on Mechanical and Abrasive Wear Behaviour of Vinyl Ester Resin. *International Journal of Applied Research in Mechanical Engineering*. (pp. 105-108).
- Ersoy, S., Taşdemir, M. (2012). Zinc oxide (ZnO), magnesium hydroxide [Mg(OH)₂] and calcium carbonate (CaCO₃) filled HDPE polymer composites. *Journal of Pure and Applied Sciences*. (pp 4,8).
- ASTM D638. (2010). Standard Test Method for Tensile Properties of Plastics, *American National Standards Institute*, Washington, ABD.
- TS EN 12770. (2004) Abrasion Resistance, *Turkish Standards Institution*, Ankara, Turkey.
- TS 11007. (1993). By a rotating cylinder Tambor Determination of Abrasion Resistance. *Turkish Standards Institution*, Ankara, Turkey.
- TS 10731. (1993). Determination of Abrasion Resistance. *Turkish Standards Institution*, Ankara, Turkey